


NEWASIA
ASIAJOINT

Grooved Joint & Pipe Fittings

KTR Test Report



NEWASIA
ASIAJOINT

<http://www.ajs.co.kr>



BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

98, Gyojuwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176867 Receipt Date : 2024.12.11.
Representative : Lee Sang-heon Test Completion Date : 2024.12.26.
Company name : NEW ASIA CO., LTD.
Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Spheroidal graphite iron castings (GCD 450-10)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/mm ²	-	459	KS B 0802:2003
Yield Strength(0.2% offset)	N/mm ²	-	303	KS B 0802:2003
Elongation	%	-	23	KS B 0802:2003
Hardness	-	-	167 HBW 10/3 000	KS B 0805:2000
Spheroidized Percent of Graphite	%	-	80	SPS-KFCA-D4302-5016 : 2014
C	%	-	3.16	KS D ISO 14707:2000
Si	%	-	2.36	KS D ISO 14707:2000
Mn	%	-	0.55	KS D ISO 14707:2000
P	%	-	0.020	KS D ISO 14707:2000
S	%	-	0.009	KS D ISO 14707:2000
Mg	%	-	0.04	KS D ISO 14707:2000

- Tensile test (KS B 0801 : Test Specimen No.4)

- Usage of Report : QUALITY CONTROL

- Next Page -

Chae Junho
Prepared by Chae Junho
Tel : 02-2092-3636

Oh Donghyun
Reviewed by Oh Donghyun
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*



QR Code for forgery



BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

98, Gyojuwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176867 Receipt Date : 2024.12.11.
Representative : Lee Sang-heon Test Completion Date : 2024.12.26.
Company name : NEW ASIA CO., LTD.
Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Spheroidal graphite iron castings (GCD 450-10)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/mm ²	-	459	KS B 0802:2003
Yield Strength(0.2% offset)	N/mm ²	-	303	KS B 0802:2003
Elongation	%	-	23	KS B 0802:2003
Hardness	-	-	167 HBW 10/3 000	KS B 0805:2000
Spheroidized Percent of Graphite	%	-	80	SPS-KFCA-D4302-5016 : 2014
C	%	-	3.16	KS D ISO 14707:2000
Si	%	-	2.36	KS D ISO 14707:2000
Mn	%	-	0.55	KS D ISO 14707:2000
P	%	-	0.020	KS D ISO 14707:2000
S	%	-	0.009	KS D ISO 14707:2000
Mg	%	-	0.04	KS D ISO 14707:2000

- Tensile test (KS B 0801 : Test Specimen No.4)

- Usage of Report : QUALITY CONTROL

- Next Page -

Chae Junho
Prepared by Chae Junho
Tel : 02-2092-3636

Oh Donghyun
Reviewed by Oh Donghyun
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*



QR Code for forgery

Sample Description

Report No : TAK-2024-176867
Test Date : 2024-12-13
Specimen Name : Spheroidal graphite iron castings (GCD 450-10)

Test Method

SPS-KFCA-D4302-5016 : 2014 By image analysis
(Minimum analyzed graphite size : 20 μm)







Equipment

Microscope : Olympus BX51M
Magnification : 100X
Image Analysis System : Clemex Vision PE

Results

Graphite spheroidization : 80 %

Shape Factor	Particle Count(-)				
	Field 1	Field 2	Field 3	Field 4	Field 5
0	18	17	21	14	11
0.73	28	35	31	40	39
0.92	92	69	91	82	69
1	34	28	22	25	27
Spheroidization(%)	80.9	80.1	77.8	80.5	82.7



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176868 Receipt Date : 2024.12.11.
Representative : Lee Sang-heon Test Completion Date : 2024.12.26.
Company name : NEW ASIA CO., LTD.
Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Stainless steel castings (SSC 13)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/mm ²	-	553	KS B 0802:2003
Yield Strength(0.2% offset)	N/mm ²	-	232	KS B 0802:2003
Elongation	%	-	47	KS B 0802:2003
Hardness	-	-	156 HBW 5/750	KS B 0805:2000
C	%	-	0.05	KS D 1652:2022
Si	%	-	0.72	KS D 1652:2022
Mn	%	-	0.98	KS D 1652:2022
P	%	-	0.032	KS D 1652:2022
S	%	-	0.020	KS D 1652:2022
Ni	%	-	8.50	KS D 1652:2022
Cr	%	-	18.56	KS D 1652:2022

- Tensile test (KS B 0801 : Test Specimen No.4)
- Usage of Report : QUALITY CONTROL

- Next Page -

Jeon Jungyu
Prepared by Jeon Jungyu
Tel : 02-2092-3639

Oh Donghyun
Reviewed by Oh Donghyun
Tel : 1577-0091(ARS ①~④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*

QR Code for forgery



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176871 Receipt Date : 2024.12.11.
Representative : Lee Sang-heon Test Completion Date : 2024.12.26.
Company name : NEW ASIA CO., LTD.
Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Rubber goods for water works service (Gasket) 70

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/cm ²	-	1 960	KS M 6613 : 2022
Elongation at Break	%	-	444	KS M 6613 : 2022
Spring Hardness Hs(Shore A)	-	-	69	KS M 6613 : 2022
Elongation at 686 N/cm ² Load	%	-	180	KS M 6613 : 2022
Tensile Set	%	-	6	KS M 6613 : 2022
Aging Test((70 ± 1) °C, 96 h)	-	-	-	KS M 6613 : 2022
-Change in Tensile Strength	%	-	-1	KS M 6613 : 2022
-Change in Elongation at Break	%	-	-8	KS M 6613 : 2022
-Change in Spring Hardness Hs	-	-	0	KS M 6613 : 2022
Compression Set((70 ± 1) °C, 22 h)	%	-	12	KS M 6613 : 2022

- Usage of Report : QUALITY CONTROL

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

- Next Page -

Ju Wonoh
Prepared by Ju Wonoh
Tel : 02-2092-3611

Kim Tae-bum
Reviewed by Kim Tae-bum
Tel : 1577-0091(ARS ①~④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*

QR Code for forgery



BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176870

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Rubber goods for water works service (Gasket) 60

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/cm ²	-	2 220	KS M 6613 : 2022
Elongation at Break	%	-	528	KS M 6613 : 2022
Spring Hardness Hs(Shore A)	-	-	60	KS M 6613 : 2022
Elongation at 686 N/cm ² Load	%	-	234	KS M 6613 : 2022
Tensile Set	%	-	6	KS M 6613 : 2022
Aging Test((70 ± 1) °C, 96 h)	-	-	-	KS M 6613 : 2022
-Change in Tensile Strength	%	-	-5	KS M 6613 : 2022
-Change in Elongation at Break	%	-	-11	KS M 6613 : 2022
-Change in Spring Hardness Hs	-	-	1	KS M 6613 : 2022
Compression Set((70 ± 1) °C, 22 h)	%	-	9	KS M 6613 : 2022

- Usage of Report : QUALITY CONTROL

- Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

- Next Page -

Ju Wonoh

Prepared by Ju Wonoh

Tel : 02-2032-3611

Kim Tae-bum

Reviewed by Kim Tae-bum

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

원본대조필



BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011

FAX 82-2-2634-1008

Report No : TAK-2024-176872

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Steel bolt (8.8)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/mm ²	-	866	KS B 0802 : 2003
Yield Strength(0.2% offset)	N/mm ²	-	588	KS B 0802 : 2003
Elongation	%	-	18	KS B 0802 : 2003
Reduction of Area	%	-	57	KS B 0802 : 2003
Hardness	-	-	24 HRC	KS B 0806 : 2000
C	%	-	0.46	KS D 1652:2022
P	%	-	0.009	KS D 1652:2022
S	%	-	0.003	KS D 1652:2022
B	%	-	0.000 2	KS D 1652:2022

- Tensile test (KS B 0801 : Test Specimen No.14A)

- Usage of Report : QUALITY CONTROL

- Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Kim Jae-Young

Prepared by Kim Jae-Young

Tel : 02-2032-3643

Oh Donghyun

Reviewed by Oh Donghyun

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery



BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

96, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176873

Representative : Lee Sang-heon

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Receipt Date : 2024.12.11.

Test Completion Date : 2024.12.26.

Sample name : Stainless-steel bolt

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength(Bolt)	N/mm ²	-	724	KS B 0241 : 2016
Stress at 0.2% permanent strain(Bolt)	N/mm ²	-	541	KS B 0241 : 2016
Elongation after fracture(Bolt)	mm	-	26.2	KS B 0241 : 2016
C	%	-	0.02	KS D 1652:2022
Si	%	-	0.38	KS D 1652:2022
Mn	%	-	1.80	KS D 1652:2022
P	%	-	0.038	KS D 1652:2022
S	%	-	0.003	KS D 1652:2022
Ni	%	-	8.06	KS D 1652:2022
Cr	%	-	18.24	KS D 1652:2022
Cu	%	-	1.11	KS D 1652:2022

Usage of Report : QUALITY CONTROL

Kim Jae-Young

Prepared by Kim Jae-Young

Tel : 02-2092-3643

Oh Donghyun

Reviewed by Oh Donghyun

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

원본대조필





BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

96, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176874

Representative : Lee Sang-heon

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Receipt Date : 2024.12.11.

Test Completion Date : 2024.12.26.

Sample name : Epoxy-powder coating

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Appearance of Coating(*)	-	-	No Defects	KS D 4317 : 2022
Adhesion of Coating(Average)(*)(*)	MPa	-	19	KS D 4317 : 2022(application
Adhesion of Coating(Minimum)(*)(*)	MPa	-	19	KS D 4317 : 2022(application
Thickness of Coating(*)	mm	-	0.4	KS D 4317 : 2022
Curing degree of Coating(*)	-	-	No Defects	KS D 4317 : 2022
Scratch Resistance of Coating(*)	-	-	No Defects	KS D 4317 : 2022

* This is the result of a test conducted using a test specimen provided by the client.

** Surface: Iron plate, Adhesive: 2-component epoxy, Test speed: below 1 MPa/s

Fracture Characteristics: Adhesive failure between coat and adhesive(-/Y)

Test equipment: PosiTest AT (Defelsko- USA)

*** Mitsubishi Pencil(H)

- Usage of Report : QUALITY CONTROL

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.

2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.

3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Kim joong yeon

Prepared by Kim joong yeon

Tel : 02-2092-3703

Lee Choong Hyu P

Reviewed by Lee Choong HyuP

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176888

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Steel butt-welding pipe fittings (SPP)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/mm ²	-	404	KS B 0802:2003
Yield Strength(0.2% offset)	N/mm ²	-	273	KS B 0802:2003
Elongation	%	-	42	KS B 0802:2003
Flattening Test	-	-	No defects	KS D 3507:2023
C	%	-	0.14	KS D 1652:2022
Si	%	-	0.01	KS D 1652:2022
Mn	%	-	0.39	KS D 1652:2022
P	%	-	0.011	KS D 1652:2022
S	%	-	0.010	KS D 1652:2022

- Tensile test (KS B 0801 : Test Specimen No.12B)

- Flattening Test (Distance between flattening plates(H) = 3/4D)

- Usage of Report : QUALITY CONTROL

- Next Page -

Chae Junho

Prepared by Chae Junho
Tel : 02-2092-3636

Oh Donghyun

Reviewed by Oh Donghyun
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

원본대조필



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176890

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Steel butt-welding pipe fittings (PS 380W)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/mm ²	-	486	KS B 0802:2003
Yield Strength(0.2% offset)	N/mm ²	-	372	KS B 0802:2003
Elongation	%	-	36	KS B 0802:2003
Flattening Test	-	-	No defects	KS D 3562:2022
C	%	-	0.19	KS D 1652:2022
Si	%	-	0.01	KS D 1652:2022
Mn	%	-	0.47	KS D 1652:2022
P	%	-	0.012	KS D 1652:2022
S	%	-	0.003	KS D 1652:2022

- Tensile test (KS B 0801 : Test Specimen No.12B)

- Flattening Test

Weld (Distance between the plates(H) = 3/4D)

Other than welding (Distance between the plates(H) = 1/4D)

- Usage of Report : QUALITY CONTROL

- Next Page -

Chae Junho

Prepared by Chae Junho
Tel : 02-2092-3636

Oh Donghyun

Reviewed by Oh Donghyun
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

BEYOND ASIAN HUB. TOWARD GLOBAL WORLD



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176891 Receipt Date : 2024.12.11.
 Representative : Lee Sang-heon Test Completion Date : 2024.12.26.
 Company name : NEW ASIA CO., LTD.
 Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Steel butt-welding pipe fittings (STS 304W)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/mm ²	-	652	KS B 0802:2003
Yield Strength(0.2% offset)	N/mm ²	-	306	KS B 0802:2003
Elongation	%	-	53	KS B 0802:2003
Flattening Test	-	-	No defects	KS D 3576:2022
C	%	-	0.06	KS D 1652:2022
Si	%	-	0.39	KS D 1652:2022
Mn	%	-	1.02	KS D 1652:2022
P	%	-	0.036	KS D 1652:2022
S	%	-	0.005	KS D 1652:2022
Ni	%	-	8.03	KS D 1652:2022
Cr	%	-	18.09	KS D 1652:2022

- Tensile test (KS B 0801 : Test Specimen No.128)
 - Flattening Test { Distance between flattening plates(H) = $\frac{((1+e)t)/(e+(t/D))}{2}$, e=0.09
 - Usage of Report : QUALITY CONTROL

- Next Page -

Jeon Jungyu
 Prepared by Jeon Jungyu
 Tel : 02-2092-3639

Oh Donghyun
 Reviewed by Oh Donghyun
 Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute


President *Kim Hyun cheol*



QR Code for forgery

원본대조필

BEYOND ASIAN HUB. TOWARD GLOBAL WORLD



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176869 Receipt Date : 2024.12.11.
 Representative : Lee Sang-heon Test Completion Date : 2024.12.26.
 Company name : NEW ASIA CO., LTD.
 Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : Rolled steels for general structure (SS275)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile Strength	N/mm ²	-	430	KS B 0802 : 2003
Yield Point	N/mm ²	-	285	KS B 0802 : 2003
Elongation	%	-	36	KS B 0802 : 2003
C	%	-	0.18	KS D 1652:2022
Si	%	-	0.23	KS D 1652:2022
Mn	%	-	0.67	KS D 1652:2022
P	%	-	0.016	KS D 1652:2022
S	%	-	0.014	KS D 1652:2022

- Tensile test (KS B 0801 : Test Specimen No.2)
 - Usage of Report : QUALITY CONTROL

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
 3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Park Geon sik
 Prepared by Park Geon sik
 Tel : 02-2092-3642

Oh Donghyun
 Reviewed by Oh Donghyun
 Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*



QR Code for forgery



BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176879

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : GROOVED JOINT (AJ520)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A	No Leakage	Client Provided Test Method
Hydrostatic Test(3.0 MPa × 1 h)	-	600A	No Leakage	Client Provided Test Method

Hydrostatic Test

-Hold the water pressure at 6.0 MPa, 4.0 MPa, 3.0 MPa for 1 h by using a pressure gauge,then check for leaks.

- Usage of Report : QUALITY CONTROL

Next Page

Jeong Hyeondo

Prepared by Jeong Hyeondo

Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

원본대조필





BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176880

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : GROOVED JOINT (AJ320)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A	No Leakage	Client Provided Test Method
Hydrostatic Test(3.0 MPa × 1 h)	-	600A	No Leakage	Client Provided Test Method

Hydrostatic Test

-Hold the water pressure at 6.0 MPa, 4.0 MPa, 3.0 MPa for 1 h by using a pressure gauge,then check for leaks.

Next Page

Jeong Hyeondo

Prepared by Jeong Hyeondo

Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176875

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : GROOVED JOINT (AJ550R)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method

〈Hydrostatic Test〉

-Hold the water pressure at 6.0 MPa for 1 h by using a pressure gauge,then check for leaks.

- Usage of Report : QUALITY CONTROL

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.

2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.

3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Jeong Hyeondo

Prepared by Jeong Hyeondo

Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

원본대조필

154 



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176876

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : GROOVED JOINT (AJ550F)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method

〈Hydrostatic Test〉

-Hold the water pressure at 6.0 MPa for 1 h by using a pressure gauge,then check for leaks.

- Usage of Report : QUALITY CONTROL

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.

2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.

3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Jeong Hyeondo

Prepared by Jeong Hyeondo

Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

Grooved Joint
Ductile fittings
Carbon Grooved fittings
STS Grooved fittings
New method for grooved joint system
Grooved machine and spare parts
Technical information
Piping manual
Material Approval Sheets

155



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008
Report No : TAK-2024-176877 Receipt Date : 2024.12.11.
Representative : Lee Sang-heon Test Completion Date : 2024.12.26.
Company name : NEW ASIA CO., LTD.
Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea
Sample name : GROOVED JOINT(AJS510R)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A	No Leakage	Client Provided Test Method

(Hydrostatic Test)
-Hold the water pressure at 6.0 MPa, 4.0 MPa for 1 h by using a pressure gauge,then check for leaks.
- Usage of Report : QUALITY CONTROL

- Next Page -

Jeong Hyeondo

Prepared by Jeong Hyeondo
Tel : 02-2082-5908

Mun Jung Sik

Reviewed by Mun Jung Sik
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*



QR Code for forgery

원본대조필



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea TEL 82-2-2164-0011 FAX 82-2-2634-1008
Report No : TAK-2024-176878 Receipt Date : 2024.12.11.
Representative : Lee Sang-heon Test Completion Date : 2024.12.26.
Company name : NEW ASIA CO., LTD.
Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea
Sample name : GROOVED JOINT(AJS510F)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method

(Hydrostatic Test)
-Hold the water pressure at 6.0 MPa for 1 h by using a pressure gauge,then check for leaks.
- Usage of Report : QUALITY CONTROL

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Jeong Hyeondo

Prepared by Jeong Hyeondo
Tel : 02-2082-5908

Mun Jung Sik

Reviewed by Mun Jung Sik
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*



QR Code for forgery



BEYOND ASIAN HUB TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011

FAX 82-2-2634-1008

Report No : TAK-2024-176882

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : GROOVED JOINT (AJ130R)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A	No Leakage	Client Provided Test Method

(Hydrostatic Test)

-Hold the water pressure at 6.0 MPa, 4.0 MPa for 1 h by using a pressure gauge, then check for leaks.

- Usage of Report : QUALITY CONTROL

- Next Page -

Jeong Hyeondo

Prepared by Jeong Hyeondo
Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

원본대조필



BEYOND ASIAN HUB TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011

FAX 82-2-2634-1008

Report No : TAK-2024-176881

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : GROOVED JOINT (AJ130F)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A	No Leakage	Client Provided Test Method

(Hydrostatic Test)

-Hold the water pressure at 6.0 MPa, 4.0 MPa for 1 h by using a pressure gauge, then check for leaks.

- Usage of Report : QUALITY CONTROL

- Next Page -

Jeong Hyeondo

Prepared by Jeong Hyeondo
Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery



BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176883

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : REDUCING JOINT (AJ730RC)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	32AX25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40AX32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50AX40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65AX50A	No Leakage	Client Provided Test Method

Hydrostatic Test

-Hold the water pressure at 6.0 MPa for 1 h by using a pressure gauge,then check for leaks.

- Usage of Report : QUALITY CONTROL

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.

2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.

3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Jeong Hyeondo

Prepared by Jeong Hyeondo

Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

160  NEWASIA ASIAJOINT



BEYOND ASIAN HUB. TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Report No : TAK-2024-176884

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : GROOVED FITTING (ELBOW)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A	No Leakage	Client Provided Test Method

Hydrostatic Test

-Hold the water pressure at 6.0 MPa, 4.0 MPa for 1 h by using a pressure gauge,then check for leaks.

- Usage of Report : QUALITY CONTROL

Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.

2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.

3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Jeong Hyeondo

Prepared by Jeong Hyeondo

Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President Kim Hyun cheol



QR Code for forgery

Grooved Joint

Ductile Grooved fittings

Carbon Grooved fittings

STS Grooved fittings

New method for grooved joint system

Grooved machine and spare parts

Technical information

Piping manual

Material Approval Sheets

161



BEYOND ASIAN HUB TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea
Report No : TAK-2024-176885
Representative : Lee Sang-heon
Company name : NEW ASIA CO., LTD.
Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea
Sample name : GROOVED FITTING (TEE)

TEL 82-2-2164-0011 FAX 82-2-2634-1008
Receipt Date : 2024.12.11.
Test Completion Date : 2024.12.26.

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	25A*25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	32A*32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40A*40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A*50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A*65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A*80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A*100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A*125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A*150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A*200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A*250A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A*300A	No Leakage	Client Provided Test Method

(Hydrostatic Test)
- Hold the water pressure at 6.0 MPa, 4.0 MPa for 1 h by using a pressure gauge, then check for leaks.
- Usage of Report : QUALITY CONTROL

- Next Page -

Jeong Hyeondo

Prepared by Jeong Hyeondo
Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*



QR Code for forgery

원본대조필



BEYOND ASIAN HUB TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea
Report No : TAK-2024-176886
Representative : Lee Sang-heon
Company name : NEW ASIA CO., LTD.
Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea
Sample name : GROOVED FITTING (REDUCER)

TEL 82-2-2164-0011 FAX 82-2-2634-1008

Receipt Date : 2024.12.11.
Test Completion Date : 2024.12.26.

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	32A*25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40A*32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A*40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A*50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A*65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A*80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A*100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A*125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A*150A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A*200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A*250A	No Leakage	Client Provided Test Method

(Hydrostatic Test)
- Hold the water pressure at 6.0 MPa, 4.0 MPa for 1 h by using a pressure gauge, then check for leaks.
- Usage of Report : QUALITY CONTROL

- Next Page -

Jeong Hyeondo

Prepared by Jeong Hyeondo
Tel : 02-2092-5908

Mun Jung Sik

Reviewed by Mun Jung Sik
Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*



QR Code for forgery



BEYOND ASIAN HUB, TOWARD GLOBAL WORLD

TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011

FAX 82-2-2634-1008

Report No : TAK-2024-176887

Receipt Date : 2024.12.11.

Representative : Lee Sang-heon

Test Completion Date : 2024.12.26.

Company name : NEW ASIA CO., LTD.

Address : 262, Neungseo-ro, Sejongdaewang-myeon, Yeosu-si, Gyeonggi-do, Republic of Korea

Sample name : GROOVED FITTING (CAP)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hydrostatic Test(6.0 MPa × 1 h)	-	25A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	32A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	40A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	50A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	65A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	80A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	100A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	125A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	150A	No Leakage	Client Provided Test Method
Hydrostatic Test(6.0 MPa × 1 h)	-	200A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	250A	No Leakage	Client Provided Test Method
Hydrostatic Test(4.0 MPa × 1 h)	-	300A	No Leakage	Client Provided Test Method

(Hydrostatic Test)

-Hold the water pressure at 6.0 MPa, 4.0 MPa for 1 h by using a pressure gauge, then check for leaks.

- Usage of Report : QUALITY CONTROL

- Next Page -

Jeong Hyeondo

Prepared by Jeong Hyeondo

Tel : 02-2082-5908

Mun Jung Sik

Reviewed by Mun Jung Sik

Tel : 1577-0091(ARS ①-④)

2024.12.26

Korea Testing & Research Institute

President *Kim Hyun cheol*



QR Code for forgery

원본대조필

